



Technical Data Sheet

MP8-0104

Yeti LB White

Non-Phthalate

Description: Yeti LB White is a non-phthalate, lead free, High Opacity, bright, high performance white that has excellent coverage on dark garments. The low tack formula allows printing through finer mesh counts without the use of viscosity modifier. Yeti LB White performs well on both automatic and manual presses. Has good bleed resistance for printing on Polyester Blends.

Substrate: Polyester Blends, Tri-Blends, Poly/Cotton, Cotton, and stretch fabrics

- Features:**
- Creamy, short body plastisol.
 - Fast Flash
 - High Opacity and great coverage
 - Good Bleed resistance at a wide temperature range
 - Bright white

Physical Properties:	Wet Ink Tack	Low
	Surface Appearance	Satin Finish
	Bleed Resistance	Good
	Opacity	High
	Gel point	160 °F
	Flash Temp & Time	230°F to 250°F
	Fusion Temp	290° - 320° F
	Squeegee Blade	70° - 80° durometer
	Mesh Count	86 – 156 mc in

Performance: Print Yeti LB white straight from the container through mesh ranging from 86 to 156 mc without modifications of the viscosity. Use finer mesh counts for softest hand and good opacity. Stir ink before use.

Storage and Handling: 65°F to 95°F avoid direct sunlight. **Never exceed temperatures above 95°F during storage.**



Technical Data Sheet

MP8-0104

Yeti LB White

Non-Phthalate

Recommendations: Stir plastisol ink before printing. Any modifiers and additives should be mixed in clean containers using clean mixer blades and ink knives. Any contamination from other ink sources could make the ink test positive for restricted phthalates. Do not dry clean, iron or bleach the printed image.

Perform fusion tests before production. Failure to cure ink properly can result in poor wash fastness, inferior adhesion, and unacceptable durability.

Adjust flash cure temperature and dwell time so ink is just dry to touch. Avoid excessive flash temperatures to protect fabric and migration of dyes. If surface is hot and tacky, the ink film has been over flashed. Reduce temperature or time to prevent an inter-coat adhesion problem.

Curing is a time and temperature process, a lower oven temperature setting with a slower belt speed while maintaining recommended ink cure temperature is always best to protect fabric, control dye migration and reduce energy consumption.

Yeti LB White can be cured between 290°F - 300°F. Running at the higher end of the temperature range and/or longer dwell times maybe required to achieve proper cure on jobs that contain cotton, high ink deposits or heavy weight garments.

***Note:** Poorly dyed polyester or too much heat in the curing process can overcome any low bleed inks ability to block the migration. For sever migration use a barrier base underlay.

Monarch Color does not knowingly add plasticizers containing the phthalates listed and outlined in California Bill 1108, CPSC HR-4040 and Oeko-tex Standard 100. The plasticizers identified may include di-(2-ethylhexyl) phthalate (DEHP), dibutyl phthalate (DBP) benzyl butyl phthalate (BBP), diisononyl phthalate (DINP), diisodecyl phthalate (DIDP), di-n-octyl phthalate (DnOP), (DIBP), Di-iso-butyl, and (DMP) Dimethylphthalate, including esters of ortho-phthalic acid and are not direct ingredients in the manufacture of Monarch plastisol direct to fabric screen printing inks. Monarch does not test the final product for amounts of the above mentioned phthalate plasticizers and esters and advises users to conduct testing for their intended use.

(Revised 3/29/19)